

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 212/14, H01M 8/10	A1	(11) International Publication Number: WO 95/08581 (43) International Publication Date: 30 March 1995 (30.03.95)
(21) International Application Number: PCT/CA94/00497 (22) International Filing Date: 14 September 1994 (14.09.94) (30) Priority Data: 124,924 21 September 1993 (21.09.93) US (71) Applicant: BALLARD POWER SYSTEMS INC. [CA/CA]; Unit 107, 980 West 1st Street, North Vancouver, British Columbia V7P 3N4 (CA). (72) Inventors: WEI, Jinzhu; 4642 Albert Street, Burnaby, British Columbia V5C 2G8 (CA). STONE, Charles; 2775 High- bury Street, Vancouver, British Columbia V6R 3T4 (CA). STECK, Alfred, E.; 3956 Westridge Avenue, West Vancou- ver, British Columbia V7V 3H7 (CA). (74) Agent: DE KOCK, Elbie, R.; Russell & DuMoulin, 1500 - 1075 West Georgia Street, Vancouver, British Columbia V6E 3G2 (CA).		(81) Designated States: AU, CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>With amended claims.</i>
(54) Title: TRIFLUOROSTYRENE AND SUBSTITUTED TRIFLUOROSTYRENE COPOLYMERIC COMPOSITIONS AND ION- EXCHANGE MEMBRANES FORMED THEREFROM (57) Abstract Polymeric compositions are derived from copolymers of α,β -trifluorostyrene with a variety of substituted α,β -trifluorostyrenes. These compositions are suitable for use as membranes, particularly as ion-exchange membranes, and most particularly as solid polymer electrolytes in electrochemical applications, such as, for example, electrochemical fuel cells.		

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

TRIFLUOROSTYRENE AND SUBSTITUTED TRIFLUOROSTYRENE
COPOLYMERIC COMPOSITIONS AND
ION-EXCHANGE MEMBRANES FORMED THEREFROM

Field Of The Invention

The present invention relates to trifluorostyrene based polymeric compositions. More particularly, the present invention relates to polymeric compositions derived from copolymers of α,β,β -trifluorostyrene with a variety of substituted α,β,β -trifluorostyrenes. These compositions are particularly suitable for use as solid polymer electrolytes in electrochemical applications, such as, for example, electrochemical fuel cells.

Background Of The Invention

A variety of membranes have been developed over the years for application as solid polymer electrolytes for fuel cells and other electrochemical applications. These polymers have typically been perfluorinated aliphatic compositions, such as those described in U.S. Patent Nos. 3,282,875 and 4,330,654. These compositions are very expensive membranes, and in the case of the '875 patent tend to exhibit poor fuel cell performance characteristic at high current densities. Alternatively, a series of low-cost polyaromatic-based systems have been investigated, such as those described in U.S. Patent Nos. 3,528,858 and 3,226,361. These materials suffer from poor chemical resistance and mechanical properties which tend to limit their use in fuel


cell applications. The investigation of other materials has involved the study of polymers containing the monomer unit α,β,β -trifluorostyrene, for example, those described in U.S. Patent No. 3,341,366 and Japanese Unexamined Patent Publication (Kokai) No. 53-26884. However, these compositions suffered from poor mechanical properties in the case of the '366 patent, and very low polymer yield in the case of the Japanese patent publication.

It is therefore an object of the invention to produce, in high yield, a low-cost ion-exchange polymer membrane with favorable chemical and mechanical properties.

It is also an object of the invention to produce an ion-exchange polymer membrane that is suitable for use in a wide variety of applications, including electrochemical applications such as fuel cells.

Summary Of The Invention

The above and other objects are achieved by a polymeric composition including:



where at least two of m, n, p and q are integers greater than zero; A₁, A₂ and A₃ are selected from the group consisting of alkyls, halogens, C_yF_{2y+1} where y is an integer greater than zero, O-R (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls), CF=CF₂, CN, NO₂ and OH;

- 3 -

and X is selected from the group consisting of SO_3H , PO_2H_2 , PO_3H_2 , $\text{CH}_2\text{PO}_3\text{H}_2$, COOH , OSO_3H , OPO_3H_2 , OArSO_3H where Ar is an aromatic, NR_3^+ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls), and CH_2NR_3^+ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls). The A_1 , A_2 , A_3 and X substituents may be located in the ortho, meta and/or para positions. The copolymer may also be binary, ternary or quaternary.

The A_1 , A_2 and A_3 substituents may be further elaborated by known means such as, for example, by hydrolysis of the CN group to form COOH or by reduction with common reducing agents (such as, for example, Raney nickel) to form a primary amine, thereby transforming the A_1 , A_2 and A_3 substituents into further "X"-type ion-exchange moieties. The resulting polymeric composition may thus comprise one or more type of ion-exchange moiety, and may also comprise both cation and anion exchange moieties.

The polymeric composition can also consist essentially of the above chemical units.

At least some of the adjacent polymers are preferably crosslinked for applications in which the resulting polymeric membrane should retard swelling.


The polymeric composition in which m and n are integers greater than zero, p and q are both zero, A_1 is fluorine or CF_3 , and X is SO_3H , is suitably formed into a membrane, and is preferably employed as an ion-exchange membrane, most preferably as a cation exchange membrane in an electrochemical fuel cell.

Brief Description of the Drawings


FIG. 1 is a plot of voltage as a function of current density in an electrochemical fuel cell employing, respectively, a Nafion 117 (DuPont's trade designation) cation exchange membrane, a Dow experimental cation exchange membrane, and a sulfonated α,β,β -trifluorostyrene copolymeric membrane.

Detailed Description Of The Preferred Embodiments

The polymeric compositions of the present invention are produced by reacting mixtures of α,β,β -trifluorostyrene having the following chemical formula:



where m is an integer greater than zero, with other monomer(s) selected from a group of substituted α,β,β -trifluorostyrenes having the following chemical formula:



where n is an integer greater than zero and A is selected from the group consisting of alkyls, halogens, $\text{C}_y\text{F}_{2y+1}$ where y is an integer greater than zero, O-R (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls),

CF=CF₂, CN, NO₂, and OH, to form a base copolymer. The "A" substituent may be located in the ortho, meta and/or para positions.

5 The above monomers are mixed in an aqueous medium containing a free radical initiator and an emulsifying agent, at temperatures in the range of about 35°C - 95°C for a time period of about 24 to 74 hours under an inert atmosphere. The base copolymers can be sulfonated, or in accordance with 10 a further aspect of this invention, may be phosphorylated, carboxylated, quaternary-aminoalkylated or chloromethylated, and further modified to yield -CH₂PO₃H₂, -CH₂NR₃⁺ where R is an alkyl, or -CH₂NAr₃⁺ where Ar is an aromatic (arene), 15 to provide a cation or anion exchange membrane. Further still, the aromatic moiety may contain a hydroxyl group which can be readily elaborated by existing methods to generate -OSO₃H and -OPO₃H₂ cationic exchange sites on the polymer.


20 In a typical sulfonation reaction used to produce a cationic exchange membrane, the copolymer is dissolved in an appropriate solvent and then reacted with a sulfonating reagent, such as chlorosulfonic acid or a Lewis acid-base complex of 25 sulfur trioxide. The solvent for such a reaction can be selected from the class consisting of chlorinated aliphatic hydrocarbons, such as dichloroethane, tetrachloroethylene and chloroform. The copolymer solution is rendered completely 30 homogeneous prior to the addition of the solution containing the sulfonating reagent. The reaction is then run within the temperature range from about 18°C plus or minus 5°C, up to the boiling point of the solvent. To ensure adequate functionalization

of the copolymer, the reaction is allowed to continue for a period of about one to about four hours, or longer.

5 The copolymers thus prepared possess favorable properties, such as high heat stability, chemical resistance and favorable mechanical properties, such as tensile strength, compared to the homopolymeric material formed from α,β,β -tri-
fluorostyrene (TFS) alone.

10 The following examples are for purposes of illustration and are not intended to limit the invention. Examples 1-9 describe the synthesis of base copolymers. Examples 10-21 describe the sulfonation of the base copolymers synthesized in
15 Examples 1-9. Example 22 sets forth the results of tests performed on three ion-exchange copolymer membranes formed from the sulfonated copolymers of the present invention, in an electrochemical fuel cell.

20 Examples 1-4 set forth the preparation of the following base copolymer:



where m and n are integers greater than zero.

Example 1

25 352 mL of deionized water and 7.05 g of dodecylamine hydrochloride were placed in a 500 mL, three-necked round bottomed flask equipped with a mechanical stirrer and a reflux condenser. N_2 was

passed through the reaction system to replace O_2 for about 1/2 hour. A charge of 44.4 g (0.28 mole, 80%) of α,β,β -trifluorostyrene (TFS) and 12.4 g (0.07 mole, 20%) of p-fluoro- α,β,β -trifluorostyrene (p-F-TFS) was added into the flask. The resulting emulsion was stirred and heated to 50°C and then 0.53 g of potassium persulfate was added into the reaction system running for a period of 48 hours. Upon completion of the reaction, the polymer emulsion was poured into a 2 L beaker containing an aqueous NaOH solution (the molar ratio of NaOH/dodecylamine hydrochloride was 5:1) and boiled for one hour to destroy the emulsifier. The mixture was filtered and the copolymer was transferred into another beaker containing methanol and stirred for 2 hours. After filtration the copolymer was redissolved in toluene and slowly precipitated in methanol. A white, fibrous copolymer was obtained and dried in a vacuum oven at 70°C, 30 Torr for several hours. The copolymerization yield was 43.3 g (76.2%) and the intrinsic viscosity ($[\eta]$) of the copolymer was 1.58 dL/g as determined in toluene at 30°C.

Example 2

The same procedure was employed as in Example 1, except that 200 mL of deionized water, 4.00 g of dodecylamine hydrochloride, 25.2 g of TFS (80%), 7.04 g of p-F-TFS (20%) and 0.30 g of potassium persulfate were used in the copolymerization. The yield was 21.8 g (67.6%) and the $[\eta]$ of the copolymer was 1.56 dL/g.

Example 3


200 mL of deionized water and 4.0 g of dodecylamine hydrochloride were placed in a 500 mL, three-necked round bottomed flask equipped with a mechanical stirrer and a reflux condenser. N₂ was passed through the reaction system to replace O₂ for about 1/2 hour. A charge of 25.2 g (0.16 mole, 80%) of TFS, 7.04 g (0.04 mole, 20%) of p-F-TFS and 0.30 g of potassium persulfate was added into the reaction flask. The resulting emulsion was stirred and heated at 50°C for a period of 48 hours. On completion of the reaction, the polymer emulsion was poured into a 2 L beaker containing an aqueous NaOH solution (the molar ratio of NaOH/dodecylamine hydrochloride was 5:1) and boiled for one hour to destroy the emulsifier. The mixture was filtered and the copolymer was transferred into another beaker containing methanol and stirred for a couple of hours. After filtration the copolymer was redissolved in toluene and slowly precipitated in methanol. A white, fibrous copolymer was obtained and dried in a vacuum oven at 70°C, 30 Torr for several hours. The yield was 20.1 g (62.3%) and the $[\eta]$ of the copolymer was 1.12 dL/g.

25

Example 4

The same procedure was employed as in Example 3, except that the reaction was run for 72 hours instead of 48 hours. The yield was 18.5 g (57.5%) and the $[\eta]$ of the copolymer was 1.12 dL/g.

Examples 5-8 set forth the preparation of the following base copolymer:



Example 5

5 The same procedure was employed as in Example 1, except that 237 mL of deionized water, 4.73 g of dodecylamine hydrochloride, 29.8 g of TFS (80%), 10.7 g of m-CF₃-TFS (20%) and 0.35 g of potassium persulfate were used in the copolymerization. The
10 yield was 29.7 g (73.4%) and the [η] of the copolymer was 1.16 dL/g.

Example 6

 The same procedure was employed as in Example 3, except that 25.2 g of TFS (80%), 9.0 g of m-CF₃-
15 TFS (20%) were used and the reaction was run for 72 hours instead of 48 hours. The yield was 19.0 g (55.5%) and the [η] of the copolymer was 1.07 dL/g.

Example 7

 The same procedure was employed as in Example 1, except that 686 mL of deionized water, 12.7 g of
20 dodecylamine hydrochloride, 80.0 g of TFS (80%), 28.7 g of m-CF₃-TFS (20%) and 0.95 g of potassium persulfate were used and the polymerization was run for 72 hours. The yield was 91.6 g (84.3%) and the
25 [η] of the copolymer was 1.28 dL/g. The ¹⁹F-NMR analysis of this copolymer was performed on a VARIAN XL-300 NMR instrument using CDCl₃ as

solvent. The results indicate that the copolymer obtained contains 27% of the m-CF₃-TFS monomer unit.


Example 8

5 The same procedure was employed as in Example 1, except that 725 mL of deionized water, 14.5 g of dodecylamine hydrochloride, 79.9 g of TFS (70%), 48.9 g of m-CF₃-TFS (30%) and 1.09 g of potassium persulfate were used and the polymerization was run
10 for 72 hours. The yield was 105.1 g (81.6%) and the [η] of the copolymer was 1.37 dL/g. The ¹⁹F-NMR analysis has shown that the copolymer contains 38% of m-CF₃-TFS monomer unit.

Example 9

15 The same procedure was employed as in Example 1, except that 189 mL of deionized water, 3.77 g of dodecylamine hydrochloride, 17.8 g of TFS (60%), 17.0 g of m-CF₃-TFS (40%) and 0.28 g of potassium persulfate were used and the polymerization was run
20 for 72 hours. The yield was 28.0 g (80.5%) and the [η] of the copolymer was 1.67 dL/g. The m-CF₃-TFS monomer unit content in the copolymer was 45% as determined by ¹⁹F-NMR.

25 Examples 10 and 11 set forth the preparation of the following sulfonated copolymer:



Example 10


A solution of 6.17 mL of ClSO_3H in 50 mL chloroform was added into a three necked flask containing a solution of 7.5 g of TFS-p-F-TFS copolymer (20% p-F-TFS) in 400 mL of chloroform over 5 minutes. The molar ratio of ClSO_3H /monomer unit was 2:1. The reaction was run at 60°C for 4 hours. The reaction mixture was then transferred into 5 L of deionized water, boiled for one hour, filtered and the product was dried in a vacuum oven at 50°C and 30 Torr. The yield was 8.8 g and the equivalent weight and water content of the sulfonated copolymer were 586 g/mol and 40%, respectively.

15

Example 11

7.5 g of TFS-p-F-TFS copolymer (20% p-F-TFS) was dissolved in 169 mL of chloroform in a three necked flask fitted with a dropping funnel, a thermocouple and an mechanical stirrer. A $\text{SO}_3/\text{O}=\text{P}(\text{OEt})_3$ complex was made by adding 10.12 mL of $\text{O}=\text{P}(\text{OEt})_3$ and 9.86 mL of SO_3 into 49.8 mL of chloroform at 0°C . The $\text{SO}_3/\text{O}=\text{P}(\text{OEt})_3$ molar ratio was 4:1 and the SO_3 /monomer unit molar ratio was 5.3:1. This complex was immediately transferred to a dropping funnel and added to the mixture over 10 minutes. The reaction was stirred at 60°C for 4 hours. The same workup procedure was used as described in Example 10. The yield was 11.4 g and the equivalent weight and water content of the sulfonated copolymer were 350 g/mol and 260%, respectively.

Examples 12-21 set forth the preparation of the following sulfonated copolymer:



Example 12

5 The same procedure was employed as in Example 11, except that an $\text{SO}_3/\text{O}=\text{P}(\text{OEt})_3$ complex containing 3.97 mL of $\text{O}=\text{P}(\text{OEt})_3$, and 3.77 mL of SO_3 in 19.4 mL of chloroform was added rapidly into the reaction system, the molar ratio of SO_3 /monomer unit was 2:1
10 and the reaction was run at room temperature for 4 hours. The yield was 8.6 g and the equivalent weight and water content of the sulfonated copolymer were 871 g/mol and 15%, respectively.

Example 13

15 A solution of 28.5 mL of ClSO_3H in 50 mL of chloroform was added over 5 minutes to a stirred solution containing 7.5 g of TFS-*m*- CF_3 -TFS copolymer (20% *m*- CF_3 -TFS) in 378 mL of chloroform at 60°C. The molar ratio of ClSO_3H /monomer unit
20 was 9.8:1 and the reaction was run at 60°C for 3 hours. A similar workup procedure was used as described in Example 10. The yield was 9.5 g and the equivalent weight and water content of the sulfonated copolymer were 350 g/mol and 776%,
25 respectively.

Example 14

7.5 g of TFS-*m*- CF_3 -TFS (20% *m*- CF_3 -TFS)

copolymer was dissolved in 160 mL of chloroform at room temperature. An $\text{SO}_3/\text{O}=\text{P}(\text{OEt})_3$ complex containing 13 mL $\text{O}=\text{P}(\text{OEt})_3$, and 12.4 mL of SO_3 in 63.9 mL of chloroform was made at 0°C and added
5 into the reaction system over 20 seconds. The molar ratio of $\text{SO}_3/\text{O}=\text{P}(\text{OEt})_3$ was 4:1 and the molar ratio of $\text{SO}_3/\text{monomer unit}$ was 7:1. The reaction was run at room temperature for 4 hours. The same workup procedure was used as described in Example
10 10. The yield was 12.8 g and the equivalent weight and water content of the sulfonated copolymer were 379 g/mol and 266%, respectively.

Example 15

15 The same procedure was employed as in Example 14, except that the $\text{SO}_3/\text{O}=\text{P}(\text{OEt})_3$ complex was made by adding 11.1 mL of $\text{O}=\text{P}(\text{OEt})_3$, and 10.7 mL of SO_3 into 54.8 mL of chloroform (the molar ratio of $\text{SO}_3/\text{monomer unit}$ was 6:1) at 0°C . The yield was
20 9.9 g and the equivalent weight and water content of the sulfonated copolymer were 399 g/mol and 151%, respectively.

Example 16

The same procedure was employed as in Example
25 14, except that the $\text{SO}_3/\text{O}=\text{P}(\text{OEt})_3$ complex was made by adding 10.1 mL of $\text{O}=\text{P}(\text{OEt})_3$, and 9.9 mL of SO_3 into 49.8 mL of chloroform (the molar ratio of $\text{SO}_3/\text{monomer unit}$ was 5.6:1) at 0°C . The equivalent weight and water content of the sulfonated
30 copolymer were 437 g/mol and 156%, respectively.

Example 17

The same procedure was employed as in Example

- 14 -

14, except that the $\text{SO}_3/\text{O}=\text{P}(\text{OEt})_3$ complex was made by adding 7.9 mL of $\text{O}=\text{P}(\text{OEt})_3$ and 7.5 mL of SO_3 into 38.7 mL of chloroform (the molar ratio of $\text{SO}_3/\text{monomer unit}$ was 4.2:1) at 0°C . The yield was 12.3 g and the equivalent weight and water content of the sulfonated copolymer were 463 g/mol and 81%, respectively.

Example 18

The same procedure was employed as in Example 14, except that the $\text{SO}_3/\text{O}=\text{P}(\text{OEt})_3$ complex was made by adding 6.0 mL of $\text{O}=\text{P}(\text{OEt})_3$ and 5.7 mL of SO_3 into 29.0 mL of chloroform (the molar ratio of $\text{SO}_3/\text{monomer unit}$ was 3.2:1) at 0°C . The yield was 9.7 g and the equivalent weight and water content of the sulfonated copolymer were 594 g/mol and 42%, respectively.

Example 19

The same procedure was employed as in Example 14, except that the $\text{SO}_3/\text{O}=\text{P}(\text{OEt})_3$ complex was made by adding 5.0 mL of $\text{O}=\text{P}(\text{OEt})_3$ and 4.7 mL of SO_3 into 24.2 mL of chloroform (the molar ratio of $\text{SO}_3/\text{monomer unit}$ was 2.6:1) at 0°C . The yield was 9.1 g and the equivalent weight and water content of the sulfonated copolymer were 825 g/mol and 21%, respectively.

Example 20

The same procedure was employed as in Example 14, except that the $\text{SO}_3/\text{O}=\text{P}(\text{OEt})_3$ complex was made by adding 4.0 mL of $\text{O}=\text{P}(\text{OEt})_3$ and 3.8 mL of SO_3 into 19.4 mL of chloroform (the molar ratio of $\text{SO}_3/\text{monomer unit}$ was 2.1:1) at 0°C . The yield was

- 15 -

8.5 g and the equivalent weight and water content of the sulfonated copolymer were 915 g/mol and 13%, respectively.

5

Example 21

The same procedure was used as in Example 14, except that the $\text{SO}_3/\text{O}=\text{P}(\text{OEt})_3$ complex was made by adding 2.0 mL of $\text{O}=\text{P}(\text{OEt})_3$ and 1.9 mL of SO_3 into 9.7 mL of chloroform (the molar ratio of SO_3 /monomer unit was 1.1:1) at 0°C . The yield was 9.1 g and the equivalent weight and water content of the sulfonated copolymer were 31,000 g/mol and 2%, respectively.

15

Example 22

Three sheets of the sulfonated TFS-m- CF_3 -TFS copolymer membranes were each bonded on opposite major surfaces to two carbon paper electrodes at room temperature under 10,000 pounds of pressure. These membrane electrode assemblies ("MEAs") were tested in the Ballard Mark IV single cell fuel cell (see U.S. Patent Nos. 4,988,583; 5,108,849; 5,170,124; 5,176,966 and 5,200,278; all incorporated herein by reference in their entirety). The results for the three sulfonated copolymer membranes tested (designated BAM3G01, BAM3G02 and BAM3G03) are shown in Table 1 below.

- 16 -

Table 1

Performance of TFS-m-CF₃-TFS Copolymer Membranes in
Ballard Mark IV Fuel Cell

<u>Amps/ft²</u>		<u>Cell Voltage (V)</u>		
		<u>BAM3G01</u>	<u>BAM3G02</u>	<u>BAM3G03</u>
5	100	0.827	0.821	0.818
	200	0.783	0.775	0.766
	300	0.739	0.736	0.719
	400	0.711	0.697	0.669
10	500	0.670	0.647	0.613
	600	0.638	0.612	0.533
	700	0.603	0.575	0.461
	800	0.573	0.540	0.255
	900	0.533	0.498	0.165
15	1000	0.494	0.438	--
	1100	0.452	0.374	--
	1200	0.393	0.355	--
	1300	0.263	--	--

- 20 The three sulfonated copolymer membranes tested had the following characteristics:
- BAM3G01: Equivalent weight 427; water content 145%; the lifetime of the MEA: 329 hrs at 500 amps/ft²
- 25 BAM3G02: Equivalent weight 447; water content 104%; the lifetime of the MEA: 4061 hrs at 500 amps/ft² (gasketed MEA)
- BAM3G03: Equivalent weight 470; water content 91%; the lifetime of the MEA: 318 hrs at 500 amps/ft²

- 30 The following operation conditions applied to the fuel cell in which the three sulfonated copolymer membranes were tested:

- 17 -

Temperature = 70°C, reactant inlet pressure 24
psi for both air and H₂, reactant
stoichiometries of 2.0 air and 1.5 H₂.

FIG. 1 is a polarization plot of voltage as a
5 function of current density in an electrochemical
fuel cell employing, respectively, a DuPont Nafion
117 cation exchange membrane, a Dow experimental
cation exchange membrane (available under the trade
designation XUS 13204.10), and the sulfonated
10 α,β,β -trifluorostyrene copolymeric membrane
designated BAM3G01 in Example 22 above. As shown
in FIG. 1, the sulfonated α,β,β -trifluorostyrene
copolymeric membrane achieved higher cell voltages
than the Dow membrane at current densities greater
15 than 800 A/ft². The Dow membrane, in turn,
achieved higher cell voltages than the Nafion 117
membrane at all current densities. Furthermore, a
sulfonated copolymer of the present invention has
exceeded 4000 hours longevity testing in an
20 electrochemical fuel cell test stand.

Copolymers formed from α,β,β -trifluorostyrene
(TFS) and m-CF₃- α,β,β -trifluorostyrene (m-CF₃-TFS)
have been produced in yields greater than 80%.


The sulfonated copolymers of the present
25 invention have the following additional advantages:

1. Flexibility to introduce a wide variety
of different ion-exchange functionalities
due to the presence of the arene groups.
2. The ability to produce a large series of
30 membranes with different equivalent
weights starting from the same base
copolymer; another flexibility provided
by the arene substituents.
3. Processibility, in that these copolymers

are soluble in a variety of common solvents, for example, N,N-dimethylformamide, dimethyl sulfoxide and N-methylpyrrolidone.

- 5 4. The ability to introduce crosslinking, using conventional techniques, such as those employed in preparing divinylbenzene polystyrene, to enhance physical and mechanical properties.

10 Crosslinked polymers of the type included in the present invention have the following chemical formula:



15 where n is greater than zero and R is fluorine or CF_3 .

 In addition to the utility of the sulfonated copolymeric membranes described herein as ion-exchange membranes for electrochemical fuel cells, the following further utilities are also
20 contemplated:

1. Proton exchange membrane based water electrolysis, which involves a reverse chemical reaction to that employed in hydrogen/oxygen electrochemical fuel
25 cells.
2. Chloralkali electrolysis, typically involving the electrolysis of a brine

solution to produce chlorine and sodium hydroxide, with hydrogen as a by-product.

- 5 3. Electrode separators in conventional batteries due to the chemical inertness and high electrical conductivity of the sulfonated copolymer membranes.
- 10 4. Ion-selective electrodes, particularly those used for the potentiometric determination of a specific ion such as Ca^{2+} , Na^{+} , K^{+} and like ions. These copolymers could also be employed as the sensor material for humidity sensors, as the electrical conductivity of an ion exchange membrane varies with humidity.
- 15 5. Ion-exchange material for separations by ion-exchange chromatography. Typical such applications are deionization and desalination of water (for example, the purification of heavy metal contaminated water), ion separations (for example, rare-earth metal ions, trans-uranium elements), and the removal of interfering ionic species.
- 20 6. Ion-exchange membranes employed in analytical preconcentration techniques (Donnan Dialysis). This technique is typically employed in analytical chemical processes to concentrate dilute ionic species to be analyzed.
- 25 7. Ion-exchange membranes in electrodialysis, in which membranes are employed to separate components of an ionic solution under the driving force of an electrical current. Electrolysis
- 30

- 5 applications include the industrial-scale desalination of brackish water, preparation of boiler feed make-up and chemical process water, de-ashing of sugar solutions, deacidification of citrus juices, separation of amino acids, and the like.
- 10 8. Membranes in dialysis applications, in which solutes diffuse from one side of the membrane (the feed side) to the other side according to their concentration gradient. Separation between solutes is obtained as a result of differences in diffusion rates across the membrane
- 15 arising from differences in molecular size. Such applications include hemodialysis (artificial kidneys) and the removal of alcohol from beer.
- 20 9. Membranes in gas separation (gas permeation) and pervaporation (liquid permeation) techniques.
- 25 10. Bipolar membranes employed in water splitting and subsequently in the recovery of acids and bases from waste water solutions.


30 While particular elements, embodiments and applications of the present invention have been shown and described, it will be understood, of course, that the invention is not limited thereto since modifications may be made by those skilled in the art, particularly in light of the foregoing teachings. It is therefore contemplated by the appended claims to cover such modifications as incorporate those features which come within the

- 21 -

spirit and scope of the invention.

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A polymeric composition comprising:



- where at least two of m, n, p and q are integers greater than zero; A₁, A₂ and A₃ are selected from the group consisting of alkyls, halogens, C_yF_{2y+1}, where y is an integer greater than zero, O-R (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls), CF=CF₂, CN, NO₂ and OH; and X is selected from the group consisting of SO₃H, PO₂H₂, PO₃H₂, CH₂PO₃H₂, COOH, OSO₃H, OPO₃H₂, OArSO₃H where Ar is an aromatic, NR₃⁺ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls) and CH₂NR₃⁺ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls).

2. The polymeric composition of claim 1 wherein at least some adjacent polymers are crosslinked.

3. The polymeric composition of claim 1 wherein m and n are integers greater than zero, p and q are both zero, A₁ is fluorine, and X is SO₃H, said composition formed into a membrane.

4. The polymeric composition of claim 3 wherein m and n are integers greater than zero, p and q are both zero, A₁ is fluorine, and X is SO₃H,

- 23 -

5 said composition employed as an ion-exchange membrane.

5. The polymeric composition of claim 4 wherein said composition is employed as an ion-exchange membrane in an electrochemical fuel cell.

6. The polymeric composition of claim 1 wherein m and n are integers greater than zero, p and q are both zero, A_1 is CF_3 , and X is SO_3H , said composition formed into a membrane.

7. The polymeric composition of claim 6 wherein said composition is employed as an ion-exchange membrane.


8. The polymeric composition of claim 7 wherein said composition is employed as a cation exchange membrane in an electrochemical fuel cell.

9. The polymeric composition of claim 1 wherein at least one of A_1 , A_2 and A_3 is selected from the group consisting of SO_3H , PO_3H_2 , $CH_2PO_3H_2$, $COOH$, OSO_3H , OPO_3H_2 , $OArSO_3H$ where Ar is an aromatic, NR_3^+ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls) and $CH_2NR_3^+$ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls), and wherein A_1 , A_2 and A_3 , when present, are each group members other than X.

5

10

10. A polymeric composition consisting essentially of:



5 where at least two of m, n, p and q are integers greater than zero; A₁, A₂ and A₃ are selected from the group consisting of alkyls, halogens, C_yF_{2y+1} where y is an integer greater than zero, O-R (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls), CF=CF₂, CN, NO₂ and OH;
 10 and X is selected from the group consisting of SO₃H, PO₂H₂, PO₃H₂, CH₂PO₃H₂, COOH, OSO₃H, OPO₃H₂, OArSO₃H where Ar is an aromatic, NR₃⁺ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls) and CH₂NR₃⁺ (where R is
 15 selected from the group consisting of alkyls, perfluoroalkyls and aryls).

11. The polymeric composition of claim 10 wherein at least some adjacent polymers are crosslinked.

12. The polymeric composition of claim 10 wherein m and n are integers greater than zero, p and q are both zero, A₁ is fluorine, and X is SO₃H, said composition formed into a membrane.

13. The polymeric composition of claim 12 wherein said composition is employed as an ion-exchange membrane.

14. The polymeric composition of claim 13 wherein said composition is employed as a cation exchange membrane in an electrochemical fuel cell.

15. The polymeric composition of claim 10 wherein m and n are integers greater than zero, p and q are both zero, A_1 is CF_3 , and X is SO_3H , said composition formed into a membrane.

16. The polymeric composition of claim 15 wherein said composition is employed as an ion-exchange membrane.


17. The polymeric composition of claim 16 wherein said composition is employed as a cation exchange membrane in an electrochemical fuel cell.

18. The polymeric composition of claim 10 wherein at least one of A_1 , A_2 and A_3 is selected from the group consisting of SO_3H , PO_3H_2 , $CH_2PO_3H_2$, $COOH$, OSO_3H , OPO_3H_2 , $OArSO_3H$ where Ar is an aromatic, NR_3^+ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls) and $CH_2NR_3^+$ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls), and wherein A_1 , A_2 and A_3 , when present, are each group members other than X.

AMENDED CLAIMS

[received by the International Bureau on 6 March 1995 (06.03.95); original claim 1 amended; original claims 3 and 6 replaced by new claim 3; original claims 4 and 7 replaced by new claim 4; original claims 5 and 8 replaced by new claim 5; original claim 9 renumbered 6 and amended; original claim 10 renumbered 7 and amended; original claim 11 renumbered 8; original claims 12 and 15 replaced by claim 9; original claims 13 and 16 replaced by claim 10; original claims 14 and 17 replaced by claim 11; original claim 18 renumbered 12 and amended; new claims 13 and 14 added; original claim 2 unchanged (5 pages)]

1. A polymeric composition comprising:



where m is an integer greater than zero and at least one of n, p and q is an integer greater than zero; A_1 , A_2 and A_3 are selected from the group consisting of alkyls, halogens, $\text{C}_y\text{F}_{2y+1}$, where y is an integer greater than zero, O-R (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls), $\text{CF}=\text{CF}_2$, CN, NO_2 and OH; and X is selected from the group consisting of SO_3H , PO_3H_2 , $\text{CH}_2\text{PO}_3\text{H}_2$, COOH , OSO_3H , OPO_3H_2 , OArSO_3H where Ar is an aromatic, NR_3^+ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls) and CH_2NR_3^+ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls).

2. The polymeric composition of claim 1 wherein at least some adjacent polymers are crosslinked.

3. A polymeric membrane comprising the polymeric composition of claim 1 wherein m is an integer greater than zero, n is an integer greater than zero, p and q are both zero, A_1 is selected from the group consisting of fluorine and CF_3 , and


X is SO₃H.

4. An ion-exchange membrane comprising the polymeric membrane of claim 3.

5. An electrochemical fuel cell comprising the ion-exchange membrane of claim 4.

6. The polymeric composition of claim 1 wherein the group from which A₁, A₂ and A₃ are selected further consists of SO₃H, PO₃H₂, CH₂PO₃H₂, COOH, OSO₃H, OPO₃H₂, OArSO₃H where Ar is an aromatic, NR₃⁺ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls) and CH₂NR₃⁺ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls), at least one of A₁, A₂ and A₃ is selected from the group consisting of SO₃H, PO₃H₂, CH₂PO₃H₂, COOH, OSO₃H, OPO₃H₂, OArSO₃H where Ar is an aromatic, NR₃⁺ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls) and CH₂NR₃⁺ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls), and wherein A₁, A₂ and A₃, when present, are each group members other than X.

7. A polymeric composition consisting essentially of:



where m is an integer greater than zero and at

- 5 least one of n, p and q is an integer greater than zero; A_1 , A_2 and A_3 are selected from the group consisting of alkyls, halogens, C_yF_{2y+1} where y is an integer greater than zero, O-R (where R is selected from the group consisting of alkyls,
- 10 perfluoroalkyls and aryls), $CF=CF_2$, CN, NO_2 and OH; and X is selected from the group consisting of SO_3H , PO_3H_2 , $CH_2PO_3H_2$, $COOH$, OSO_3H , OPO_3H_2 , $OArSO_3H$ where Ar is an aromatic, NR_3^+ (where R is selected from the group consisting of alkyls,
- 15 perfluoroalkyls and aryls) and $CH_2NR_3^+$ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls).

8. The polymeric composition of claim 7 wherein at least some adjacent polymers are crosslinked.

9. A polymeric membrane comprising the polymeric composition of claim 7 wherein m is an integer greater than zero, n is an integer greater than zero, p and q are both zero, A_1 is selected from the group consisting of fluorine and CF_3 , and X is SO_3H .
- 5


10. An ion-exchange membrane comprising the polymeric membrane of claim 9.

11. An electrochemical fuel cell comprising the ion-exchange membrane of claim 10.

12. The polymeric composition of claim 7 wherein the group from which A_1 , A_2 and A_3 are selected further consists of SO_3H , PO_3H_2 , $CH_2PO_3H_2$,


- COOH, OSO₃H, OPO₃H₂, OArSO₃H where Ar is an aromatic, NR₃⁺ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls) and CH₂NR₃⁺ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls), at least one of A₁, A₂ and A₃ is selected from the group consisting of SO₃H, PO₃H₂, CH₂PO₃H₂, COOH, OSO₃H, OPO₃H₂, OArSO₃H where Ar is an aromatic, NR₃⁺ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls) and CH₂NR₃⁺ (where R is selected from the group consisting of alkyls, perfluoroalkyls and aryls), and wherein A₁, A₂ and A₃, when present, are each group members other than X.

13. A polymeric composition comprising:



- where at least one of n, p and q is an integer greater than zero; and A₁, A₂ and A₃ are selected from the group consisting of O-R (where R is selected from the group consisting of C_yH_{2y+1} and C_yF_{2y+1}, where y is an integer greater than three, and aryls), CF=CF₂, CN, NO₂ and OH.

14. A polymeric composition consisting essentially of:



- 5 where at least one of n , p and q is an integer greater than zero; and A_1 , A_2 and A_3 are selected from the group consisting of O-R (where R is selected from the group consisting of C_yH_{2y+1} and C_yF_{2y+1} , where y is an integer greater than three, and aryls), $CF=CF_2$, CN , NO_2 and OH .

1/1




Figure 1.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/CA 94/00497

A. CLASSIFICATION OF SUBJECT MATTER		
IPC6: C08F 212/14, H01M 8/10 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
IPC6: C08F, H01M		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, A, 3341366 (R.B. HODGDON, JR., ET AL), 12 Sept 1967 (12.09.67) --	1-18
A	US, A, 4012303 (VINCENT F. D'AGOSTINO ET AL), 15 March 1977 (15.03.77) -- -----	1-18
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input checked="" type="checkbox"/> See patent family annex.		
<p>* Special categories of cited documents</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&" document member of the same patent family</p>		
Date of the actual completion of the international search		Date of mailing of the international search report
15 December 1994		06.01.95
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL-2280 HV Rijswijk Tel (+31-70) 340-2040, Tx. 31 651 epo nl, Fax (+31-70) 340-3016		Authorized officer JACK HEDLUND

INTERNATIONAL SEARCH REPORT

Information on patent family members

26/11/94

International application No.

PCT/CA 94/00497

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A- 3341366	12/09/67	BE-A- 668486	16/12/65
		CH-A- 463462	00/00/00
		DE-A,B,C 1570681	12/03/70
		FR-A- 1452148	00/00/00
		GB-A- 1096879	00/00/00
		NL-A- 6510859	21/02/66
		US-A- 3442825	06/05/69
<hr/>			
US-A- 4012303	15/03/77	BE-A- 836970	22/06/76
		DE-A- 2558393	24/06/76
		FR-A- 2295982	23/07/76
		GB-A- 1498990	25/01/78
		JP-A- 51089881	06/08/76
		NL-A- 7514956	25/06/76
		SE-A- 7514517	24/06/76
		US-A- 4107005	15/08/78
		US-A- 4113922	12/09/78
<hr/>			

THIS PAGE BLANK (USPTO)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)